

5052 H14 Aluminum Sheet

Properties

General

Property	Temperature	Value
Density	23.0 °C	2.7 g/cm³

Mechanical

Property	Temperature	Value	Comment
Elastic modulus	23.0 °C	70 GPa	
Elongation	23.0 °C	4.6 %	
Plane-Strain Fracture Toughnes	23.0 °C	22 - 35 MPa·√m	Typical for Wrought 5000 Series Aluminium
Poisson's ratio	23.0 °C	0.33 [-]	Typical for Wrought 5000 Series Aluminium
Shear modulus	23.0 °C	26 - 26.5 GPa	Typical for Wrought 5000 Series Aluminium
Tensile strength	23.0 °C	250 MPa	
Yield strength	23.0 °C	210 MPa	

Thermal

Property	Temperature	Value	Comment
	23.0 °C	2.4E-5 1/K	

Coefficient of thermal expansion

Max service temperature	150 °C	Typical for Wrought 5000 Series Aluminium
-------------------------	------------------------	---

Melting point	610 °C
---------------	------------------------

Specific heat capacity	23.0 °C	900 J/(kg·K)
------------------------	---------	------------------------------

Thermal conductivity	23.0 °C	140 W/(m·K)
----------------------	---------	-----------------------------

Electrical

Property	Temperature	Value	Comment
Electrical conductivity	23.0 °C	1.80E+7 - 3.10E+7 S/m	Typical for Wrought 5000 Series Aluminium
Electrical resistivity	23.0 °C	3.3E-8 - 5E-8 Ω·m	Typical for Wrought 5000 Series Aluminium

Chemical properties

Property	Value
Aluminium	95.8 - 97.7 %
Chromium	0.15 - 0.35 %
Copper	0 - 0.1 %
Iron	0 - 0.4 %
Magnesium	2.2 - 2.8 %
Manganese	0 - 0.1 %
Other	0 - 0.15 %
Silicon	0 - 0.25 %

Zinc

[0 - 0.1 %](#)

Technological properties

Property

Workability

Good workability.
