



6063 T4 Aluminum Sheet

[Metal](#) > [Aluminium](#) > [Wrought Aluminium](#) > [6000 Series](#) > EN AW-6063 T4

EN AW-6063 T4

Equivalent Materials

EN AW-6063

DIN AlMg0.7Si

AA 6063



.HENAN LICHEN ALUMINUM CO.,LTD

Properties

Dimension

Property	Value
Thickness	25 mm

Mechanical

Property	Temperature	Value
Elongation	23.0 °C	14 %
Elongation A50	23.0 °C	12 %
Hardness, Brinell	23.0 °C	50 [-]
Tensile strength	23.0 °C	130 MPa
Yield strength Rp0.2	23.0 °C	65 MPa

Chemical properties

Property	Value
Aluminium	balance
Chromium	0.1 %
Copper	0.1 %
Iron	0.35 %
Magnesium	0.45 - 0.9 %
Manganese	0.1 %
Other	0.05 - 0.15 %
Silicon	0.2 - 0.6 %
Titanium	0.1 %
Zinc	0.1 %